

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Godfrey Hirst Aust Pty Ltd
7 Factories Road
South Geelong VIC 3220

Test Number : 22-001025
Issue Date : 21/04/2022
Print Date : 21/04/2022
Order Number : AW3H

Sample Description Clients Ref : "KLVP 4.5mm/0.3mm"
Vinyl Plank
Colour : Timber look
End Use : Flooring
Nominal Composition : Vinyl
Nominal Thickness : 4.5mm(0.3mm wear layer)



266239

57408

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Godfrey Hirst Aust Pty Ltd
7 Factories Road
South Geelong VIC 3220

Test Number : 22-001025
Issue Date : 21/04/2022
Print Date : 21/04/2022
Order Number : AW3H

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 29-03-2022

Date Tested 20-04-2022

CHF Value	1	2	3	Mean
Length	7.7	8.6	9.0	8.4 kW/m ²
Width	10.3	-	-	- kW/m ²

Smoke Value	1	2	3	Mean
Length	182	168	162	171 % .min
Width	151	-	-	- % .min

Observations:

Melting Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

HF30 not reported as flame out time occurred before 30 minutes.

Each specimen was adhered to Damtec 2mm Colour underlay , and then bonded 6mm thick fibre reinforced board using Mapei Ultrabond ECO VS90 Plus adhesive and clamped prior to testing.

266239

57408

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR